



AGM Container Controls, Inc.  
 3526 E. Fort Lowell Rd., Tucson, AZ 85716  
 Tel: 520-881-2130  
 Email: sales@agmcontainer.com  
 Website: www.agmcontainer.com

**PRODUCT SPECIFICATIONS**

**AGM Part Number 920106**

Activated Alumina, 1/8", 3/16", 1/4" Beaded

**CHEMICAL FORMULA**      Al<sub>2</sub>O<sub>3</sub> • nH<sub>2</sub>O

**PRODUCT DESCRIPTION**

Activated alumina is a synthetically produced aluminum oxide in a smooth spherical form with a high crush strength. It is highly porous and can have a surface area greater than 300 m<sup>2</sup>/g. It is an excellent desiccant for liquids and gases and can achieve dew points from -40°F to 100°F depending on the operating conditions and the design of the dryer. Activated alumina will adsorb all molecules to some degree but will preferentially adsorb the molecules with the highest polarity.

TYPICAL CHEMICAL COMPOSITION (Wt %)	
Al <sub>2</sub> O <sub>3</sub>	92.7%
SiO <sub>2</sub>	0.02%
FE <sub>2</sub> O <sub>3</sub>	0.02%
NA <sub>2</sub> O	0.30%

	TYPICAL PROPERTIES			
	1/16" (1.5-2mm)	1/8" (3.2mm)	3/16" (4.7 mm)	1/4" (6.4 mm)
Surface Area, m <sup>2</sup> /g	> 300	> 300	> 300	> 300
Total Pore Volume, cc/g	0.5	0.5	0.5	0.5
Bulk Density, lbs/ft <sup>3</sup> (kg/m <sup>3</sup> )	≥ 43 (690)	≥ 47 (753)	≥ 47 (753)	≥ 47 (753)
Crush Strength, lbs (N)	≥ 19 (87)	≥ 27 (120)	≥ 42 (180)	≥ 67 (300)
LOI (250-1100°C), Wt %	< 7	< 7	< 7	< 7
Abrasion Loss, Wt %	≤ 0.5	≤ 0.5	≤ 0.5	≤ 0.5

**TYPICAL APPLICATIONS**

As a desiccant in compressed air dryers; water purification to remove fluoride, arsenic and selenium; removal of degradation acids from transformer oils, lubricating oils, and refrigerants; natural gas drying; liquefied natural gas drying.

**PACKAGING INFORMATION**

Bags                    50 lb (23 kg)  
 Drums                Fill weights to order specification  
 Super Sacks        Fill weights to order specification

**HANDLING AND STORAGE RECOMMENDATIONS**

Store activated alumina in a dry location to prevent premature water adsorption. Reseal packages after opening to prevent contamination and unintended water adsorption. We recommend that you rotate stock so oldest material is used first.

**HEALTH & SAFETY INFORMATION**

Health and Safety Information is available on the product MSDS.